

**0 AMENDMENTS TO THE SPECIFICATION:**

At page 15, line 1, prior to the paragraph starting with "substantially linear ethylene/ $\alpha$ -olefin...", please insert the following:

One factor that influences the overall MWD is the difference between the molecular  
5 weights of the HMW component and the LMW component. In some embodiments, the ratio of  
the molecular weights of the polymer produced by one catalyst to the molecular weight of the  
polymer produced by the other catalyst,  $M_{wh}/M_{wl}$ , is about 1 to 20.

Another factor that can have a substantial effect on the overall MWD is the "polymer  
split" of the composition. A "polymer split" is defined as the weight fraction of the high  
molecular weight polymer component in a polymer composition. The relative fraction of the  
high and low molecular weight components are determined from the deconvoluted GPC peak.  
The polymer composition of the present invention has a split of about 30% to about 70%,  
preferably of from about 40% to about 60%, more preferably from about 45% to about 55%.

In the process, a high molecular weight catalyst is defined relative to a low molecular  
15 weight catalyst. A high molecular weight catalyst refers to a catalyst which produces a polymer  
with a high weight-average molecular weight  $M_{wh}$  from the monomers and any comonomers of  
choice under a set of given polymerization conditions, whereas a low molecular weight catalyst  
refers to a catalyst which produces a polymer with a low weight average molecular weight  
 $M_{wl}$  from the same monomer and comonomers under substantially the same polymerization  
20 conditions. Therefore, the terms "low molecular weight catalyst" and "high molecular weight  
catalyst" used herein do not refer to the molecular weight of a catalyst; rather, they refer to a  
catalyst's ability to make a polymer with a low or high molecular weight. The intrinsic  
molecular weight differences in the polymer produced by the chosen high and low molecular  
weight catalysts produces the "polymer split" of the composition.

25 Thus, a high molecular weight catalyst and a low molecular weight catalyst are  
determined with reference to each other. One does not know whether a catalyst is a high  
molecular weight catalyst or a low molecular weight catalyst until after another catalyst is also  
selected. Therefore, the terms "high molecular weight" and "low molecular weight" used herein